



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C07F 3/00, 5/00, 5/02, 5/06, 7/02, 7/22, 7/28, 7/30, 9/02, 9/66, 9/94	A1	(11) International Publication Number: WO 00/53611 (43) International Publication Date: 14 September 2000 (14.09.00)
(21) International Application Number: PCT/US00/06293 (22) International Filing Date: 10 March 2000 (10.03.00) (30) Priority Data: 60/123,599 10 March 1999 (10.03.99) US (71) Applicant: COLORADO STATE UNIVERSITY RESEARCH FOUNDATION [US/US]; P.O. Box 483, Fort Collins, CO 80522 (US). (72) Inventors: STRAUSS, Steven, H.; 5849 Plateau Court, Fort Collins, CO 80526 (US). NOLAN, Benjamin, G.; 1225 W. Prospect Road #J202, Fort Collins, CO 80526 (US). FAUBER, Benjamin, P.; 260 W. Prospect Road #102, Fort Collins, CO 80526 (US). (74) Agents: CHA, Don, D. et al.; Sheridan Ross P.C., Suite 1200, 1560 Broadway, Denver, CO 80202-5141 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: WEAKLY COORDINATING ANIONS CONTAINING POLYFLUOROALKOXIDE LIGANDS		
(57) Abstract <p>A compound comprising a polyfluorinated anion and the use thereof is provided. Specifically, the present invention provides a compound comprising an anion which comprises a polyfluorinated alkoxide coordinated to a transition metal, or a Group III, IV or V element.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

WEAKLY COORDINATING ANIONS CONTAINING POLYFLUOROALKOXIDE LIGANDS

FIELD OF THE INVENTION

5 The present invention relates to a compound containing polyfluoroalkoxides and the use thereof, in particular, for use as an electrolyte in batteries and other electrochemical devices.

BACKGROUND OF THE INVENTION

10 A compound containing a weakly coordinating anion (i.e., an anion that coordinates only weakly with a cation) is useful in a variety of applications including as an electrolyte and a counter-ion for a catalyst in a variety of organic reactions. Some of the useful catalysts containing a weakly coordinating anion are described by Barbarich, *et al.* in "LiAl(OC(Ph)(CF₃)₂)₄: A Hydrocarbon-Soluble Catalyst For Carbon-Carbon
15 Bond-Forming Reactions", *Organometallics*, **1996**, *15*, 3776, which is incorporated herein in its entirety.

Investigations of very reactive metal and nonmetal cations continues to spur the development of new weakly coordinating anions. *See, for example*, Bochmann, *Angew. Chem., Int. Ed. Engl.* **1992**, *31* 1181; Strauss, *Chem. Rev.* **1993**, *93*, 927, Strauss,
20 *Chemtracts-Inorganic Chem.* **1994**, *6*,1; and Seppelt, *Angew. Chem., Int. Ed. Engl.* **1993**, *32*, 1025. One of the most important uses of weakly coordinating anions is to enhance the catalytic activity of metal cations. Two examples that have received considerable attention recently are metallocene-catalyzed olefin polymerization, and lithium-catalyzed Diels-Alder reactions and 1,4-conjugate addition reactions. *See* Turner, European Patent
25 Appl. No. 277,004, 1988; Pellecchia *et al.*, *Makromol. Chem., Rapid Commun.* **1992**, *13*, 265; DuBay *et al.*, *J. Org. Chem.* **1994**, *59*, 6898; Saidi *et al.*, *Chem. Ber.* **1994**, *127*, 1761; Kobayashi *et al.*, *Chem. Lett.* **1995**, 307; and Arai *et al.*, *Angew. Chem., Int. Ed. Engl.* **1996**, *15*, 3776.

Useful anions must not only be weakly coordinating, they must also be stable with
30 respect to oxidation and/or fragmentation in the presence of highly electrophilic cations. In addition, an ideal weakly coordinating anion should have a single negative charge dispersed over a large surface composed of relatively nonpolar bonds to weakly basic atoms such as hydrogen or the halogens. Weakly coordinating anions which conform to

many, but not all, of these criteria include $B(Ar_f)_4^-$ ($Ar_f = C_6F_5$ or $3,5-C_6H_3(CF_3)_2$), $CB_{11}H_{12-n}X_n^-$ ($X = H, Me, Cl, Br, F$ or I), $CB_9H_{10-n}X_n^-$ ($X = H, F, Cl$, or Br), and $M(OTeF_5)_n^-$ ($n = 4, 5, 6$; $M = B$; $n = 6, 7$; $M = Nb, Sb$).

5 All of the anions mentioned above have limitations. Some are too strongly coordinating for specific applications. Some are unstable under the harsh chemical conditions where they would be employed. For example, the fluorinated derivatives of BPh_4^- can react with strongly electrophilic cations, causing (i) cleavage of a C-F bond and formation of a bond between the fluorine atom and the cation or (ii) transfer of a fluoroaryl group to the cation. In either case, the cation is no longer reactive or
10 catalytically active.

Other weakly coordinating anions, such as ClO_4^- , BF_4^- , PF_6^- , SbF_6^- , $B(OTeF_5)_4^-$, and $Nb(OTeF_5)_6^-$, are not thermally and/or hydrolytically stable. In addition, lithium salts of such anions, including $LiCF_3SO_3$, have low electrical conductivity in some organic solvents, especially organic solvents that are stable in the presence of strong reducing
15 agents such as metallic lithium and related lithium-containing battery anode solutions. Furthermore, some lithium salts, such as lithium triflate ($LiCF_3SO_3$), cause corrosion of the aluminum current collectors in batteries, while some lithium salts, such as $LiPF_6$, are known to be unstable at temperatures as low as $70^\circ C$ and decompose over time.

Still other anions containing boron atoms, and anions containing a carbon atom
20 and a cluster of boron atoms, such as carboranes (*e.g.*, CB_5 , CB_9 , CB_{11}), are not particularly weakly coordinating because the salts formed therefrom contain at most only one fluorine atom which is bonded to a boron atom.


Recently, polyfluorinated carborane anions that are weakly coordinating and are thermally and/or hydrolytically stable have been disclosed in commonly assigned U.S.
25 Patent Application No. 09/049,420, filed March 27, 1998. In addition, one particular class of compounds containing polyfluoroalkoxide ligands and the use thereof has been disclosed in commonly assigned PCT Patent Application No. PCT/US98/19268, filed September 11, 1998, and commonly assigned U.S. Patent Application No. 09/151,852, filed September 11, 1998, disclosures of which are incorporated herein by reference in
30 their entirety.

Despite the recent advances in weakly coordinating anions, there still is a need for new weakly coordinating anions. There is also a need for weakly coordinating anions having a high electrical conductivity in an organic solvent. There is also a need for weakly coordinating anions that are stable in solution and in the solid state.

5

SUMMARY OF THE INVENTION

One embodiment of the present invention provides a compound comprising a monoanion of the formula:



10 and uses thereof,

where

M_1 is a transition metal, or a Group III, IV or V element;

each Z is independently O, S, or NR_6R_7 ;

each X is independently a halide;

15 each R_1 is independently a bond or C_1 - C_4 alkylene;

each of R_2 , R_3 and R_4 is independently H, F, fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl, C_3 - C_{10} cycloalkyl, fluorinated C_3 - C_{10} cycloalkyl, C_1 - C_{10} alkyl or C_4 - C_{20} aryl, provided at least one of R_2 , R_3 and R_4 is F, fluorinated C_1 - C_{10} alkyl, fluorinated C_3 - C_{10} cycloalkyl, or fluorinated C_4 - C_{20} aryl;

20 each R_5 is independently fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl, C_4 - C_{20} aryloxy, fluorinated C_4 - C_{20} aryloxy, C_1 - C_{10} alkoxide or fluorinated C_1 - C_{10} alkoxide;

each of R_6 and R_7 is independently H or C_1 - C_{10} alkyl;

each of a, b and c is independently an integer from 0 to 4,


25 provided the sum of a, b and c is an integer from 2 to 8; and

n is 1 or 2; and

provided that when R_2 is a fluorinated C_1 - C_4 alkyl, R_1 is a bond, b, and c are 0,

and R₃ is C₁-C₁₀ alkyl or fluorinated C₁-C₁₀ alkyl then R₄ is F, fluorinated C₁-C₁₀ alkyl or fluorinated C₄-C₂₀ aryl, preferably F, fluorinated C₁-C₁₀ alkyl or fluorinated C₄-C₂₀ aryl.

Another embodiment of the present invention provides a compound comprising
 5 an anion of the formula:



wherein

M₁ is a transition metal, or a Group III, IV or V element;

L is a halide, C₁-C₁₀ alkyl, fluorinated C₁-C₁₀ alkyl, C₄-C₂₀ aryl, fluorinated
 10 C₄-C₂₀ alkyl or a moiety of the formula -Z₃-R₁₁;

d is an integer from 0 to 4;

e is an integer from 1 to 3;

the sum of d and e is an integer from 1 to 6;

n is 1 or 2;

15 each of Z₁, Z₂ and Z₃ is independently O, S, or NR₆R₇;

each of R₆ and R₇ is independently H or C₁-C₁₀ alkyl;

each R₉ is independently C₁-C₃₀ alkylene, fluorinated C₁-C₃₀ alkylene, substituted C₁-C₃₀ alkylene, C₃-C₁₀ cycloalkylene, fluorinated C₃-C₁₀ cycloalkylene, C₄-C₂₀ arylene or fluorinated C₄-C₂₀ arylene;

20 each of R₈ and R₁₀ is a bond, or a moiety of the formula -[C(R₁₂R₁₃)]_x;

each x is independently an integer from 1 to 4;

each of R₁₂ and R₁₃ is independently H, F, C₁-C₄ alkyl or fluorinated C₁-C₄ alkyl; and

25 each R₁₁ is independently C₁-C₁₀ alkyl, fluorinated C₁-C₁₀ alkyl, C₄-C₂₀ aryl, or fluorinated C₄-C₂₀ aryl;


provided at least one of R₈ and R₁₀ is a moiety of the formula -C(R₁₂R₁₃)- and at least one of R₁₂ and R₁₃ is F or fluorinated C₁-C₄ alkyl.

The present invention also provides an electrolyte for an electrochemical device,

comprising the anion of the above described formula having a counter cation M where M is a metal cation, a phosphonium cation, an ammonium cation or a sulfonium cation. Preferably M is Li cation.

5 DETAILED DESCRIPTION OF THE INVENTION


The present invention provides a compound comprising an anion of the formula:



I

and uses thereof, where M_1 is a transition metal, or a Group III, IV or V element, preferably M_1 excludes Cu; each Z is independently O, S, or NR_6R_7 ; each X is independently a halide; each R_1 is independently a bond or C_1 - C_4 alkylene; each of R_2 , R_3 and R_4 is independently H, F, fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl, C_3 - C_{10} cycloalkyl, fluorinated C_3 - C_{10} cycloalkyl, C_1 - C_{10} alkyl or C_4 - C_{20} aryl, provided at least one of R_2 , R_3 and R_4 is F, fluorinated C_1 - C_{10} alkyl, fluorinated C_3 - C_{10} cycloalkyl, or fluorinated C_4 - C_{20} aryl; each R_5 is independently fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl, C_4 - C_{20} aryloxy, fluorinated C_4 - C_{20} aryloxy, C_1 - C_{10} alkoxide or fluorinated C_1 - C_{10} alkoxide; each of R_6 and R_7 is independently H or C_1 - C_{10} alkyl; each of a, b and c is independently an integer from 0 to 4, provided the sum of a, b and c is an integer from 2 to 8; and n is 1 or 2; provided that when R_2 is a fluorinated C_1 - C_4 alkyl, R_1 is a bond, b, and c are 0, and R_3 is C_1 - C_{10} alkyl or fluorinated C_1 - C_{10} alkyl then R_4 is F, fluorinated C_1 - C_{10} alkyl or fluorinated C_4 - C_{20} aryl, preferably F, fluorinated C_1 - C_{10} alkyl or fluorinated C_4 - C_{20} aryl.

The present invention also provides a compound comprising an anion of the formula:




II

where M_1 is a transition metal, or a Group III, IV or V element; L is a halide, C_1 - C_{10} alkyl, fluorinated C_1 - C_{10} alkyl, C_4 - C_{20} aryl, fluorinated C_4 - C_{20} alkyl or a moiety of the formula $-Z_3-R_{11}$;

d is an integer from 0 to 4; e is an integer from 1 to 3; the sum of d and e is an integer from 1 to 6; n is 1 or 2; each of Z_1 , Z_2 and Z_3 is independently O, S, or NR_6R_7 ; each of R_6 and R_7 is independently H or C_1 - C_{10} alkyl; each R_9 is independently C_1 - C_{30} alkylene, fluorinated C_1 - C_{30} alkylene, substituted C_1 - C_{30} alkylene, C_3 - C_{10} cycloalkylene, fluorinated C_3 - C_{10} cycloalkylene, C_4 - C_{20} arylene or fluorinated C_4 - C_{20} arylene; each of R_8 and R_{10} is a bond, or a moiety of the formula $-[C(R_{12}R_{13})]_x$; each x is independently an integer from 1 to 4; each of R_{12} and R_{13} is independently H, F, C_1 - C_4 alkyl or fluorinated C_1 - C_4 alkyl; and each R_{11} is independently C_1 - C_{10} alkyl, fluorinated C_1 - C_{10} alkyl, C_4 - C_{20} aryl, or fluorinated C_4 - C_{20} aryl; provided at least one of R_8 and R_{10} is a moiety of the formula $-C(R_{12}R_{13})-$ and at least one of R_{12} and R_{13} is F or fluorinated C_1 - C_4 alkyl.

Preferably, the compound of the present invention has at least two polyfluorinated alkoxide groups bonded to M_1 . As used herein, a "polyfluorinated anion" refers to an anion of the above described formula.

The polyfluorinated anions of the present invention themselves do not necessarily comprise chemical compounds. Indeed, in an isolable compound, anions must be paired with cations to maintain electroneutrality. Thus, compounds of the present invention are, more accurately, of the formulas:



where M is a cation having a valence of from 1 to 4. M can be any cation including a cation derived from an alkali metal; alkaline-earth metal; transition metal such as Ag, Zn, Cu, Co, Fe, Mn, Cr, V, Ti, Zr, Rh, Pd, Cd, Hg, Os, Pt, Y, Nb, Sc, Ta, Hf, and Mo; lanthanide and actinide series metal; ammonium moieties such as ammonium, tetrahydrocarbyl ammonium, *e.g.*, tetrabutyl ammonium and tetraethyl ammonium, trihydrocarbyl ammonium, *e.g.*, triethyl ammonium, diisopropyl ethyl ammonium and trimethyl ammonium, dihydrocarbyl ammonium, nitrogen heteroaromatic cation such as 2,6-lutidinium, methyl 2,6-lutidinium, methyl pyridinium and pyridinium, and imminium cation; phosphonium moieties including tetraalkylphosphonium, tetraaryl phosphonium and phosphonium ions containing a mixture of alkyl and aryl groups; sulfonium moieties such as sulfonium ions containing alkyl, aryl or mixtures thereof; and other suitable cations such as thallium. Furthermore, M can be a relatively stable carbocation such as a trityl moiety and related carbocations (*e.g.*, R_3C^+); and other known cations such as hydronium (H_3O^+), H_5O_2^+ , $(\text{Et}_2\text{O})_n\text{H}^+$, H_9O_4^+ , and formylium (HCO^+). Preferably, the cation (*i.e.*, M) is selected from the group consisting of thallium, alkali metal and alkaline earth metal cations, ammonium, monohydrocarbyl ammonium, dihydrocarbyl ammonium, trihydrocarbyl ammonium, tetrahydrocarbyl ammonium, nitrogen heteroaromatic cation, tetrahydrocarbyl phosphonium, hydronium, formylium, and trityl and related carbocations; more preferably from the group consisting of trityl and related carbocations, thallium, tetrahydrocarbyl ammonium, alkali metal cations, and nitrogen heteroaromatic cation; and most preferably from the group consisting of trityl, Li^+ , Tl^+ , 2,6-lutidinium, tetraethylammonium, sodium, potassium, and N-methyl-2,6-lutidinium. As used in this invention, a "hydrocarbyl" refers to a compound having at least one carbon atom. Such compounds include aryl, alkyl, alkenyl and alkynyl. Moreover, hydrocarbyl can be straight

chain, branched, or cyclic. Hydrocarbonyl can also be substituted with other non hydrogen or carbon atoms such as halide, oxygen, sulfur, nitrogen or phosphorus.

It will be appreciated that a molar ratio of a cation to a polyfluorinated anion of the present invention depends on the valence of the cation. This is reflected in the values p and k, for example, if both the cation and the anion are monovalent, then k and p are 1, and there will be a 1:1 molar ratio between the cation and the polyfluorinated anion of the present invention. Whereas if the cation is divalent and the anion is monovalent, then k is 2 and p is 1, and there will be a 1:2 molar ratio between the cation and the polyfluorinated anion of the present invention. Preferably, k is an integer from 1 to 4, more preferably 1 to 3, still more preferably k is 1 or 2, and most preferably 1. Preferably p is 1 or 2 and more preferably 1.

It should be appreciated that because the polyfluorinated anions of the present invention are weakly associating (*i.e.*, coordinating) anions, a cation associated with a polyfluorinated anion can be readily exchanged with another cation by any of the known methods including ion exchange chromatography and other ion exchange methods.

As used in this invention, Group III, IV and V elements are those elements which are listed in the Group III, IV and V of the periodic table, respectively. For example, Group III elements are B, Al, Ga, In and Tl; Group IV elements are C, Si, Ge, Sn, and Pb; and Group V elements are N, P, As, Sb and Bi.

With reference to formulas I-IV described herein:

Preferably M_1 is selected from the group consisting of Al, B, V, Ti, Si, Zr, Ge, Sn, Cu, Y, Zn, Ga, Nb, Ta, Bi, P, As, Sc, Hf and Sb, more preferably from the group consisting of Al, B, V, Ti, Si, Zr, Ge, Sn, Y, Zn, Ga, Nb, Ta, Bi, P, As, Sc, Hf and Sb, still more preferably from the group consisting of Al, B, Nb and Ta, and most preferably from the group consisting of Al and B.

Preferably, Z, Z_1 , Z_2 and Z_3 are O.

Preferably n is 1.

Preferably a is 1, 3 or 4, more preferably 4.

Preferably b is 0 or 1.

Preferably c is 0 or 3.

Preferably the sum of a, b and c is an integer from 2 to 8, more preferably an integer from 4 to 8, still more preferably an integer from 4 to 6, and most preferably 4.

Preferably X is fluoride.

5

Preferably R₅ is fluorinated C₄-C₂₀ aryl or fluorinated C₄-C₂₀ aryloxy, more preferably fluorinated phenyl or phenoxide, and most preferably 2-trifluoromethylphenoxide, 3-trifluoromethylphenoxide, 4-trifluoromethylphenoxide, pentafluorophenoxide, or pentafluorophenyl.

Preferably R₁ is a bond or methylene.

10

Preferably each of R₂, R₃ and R₄ is independently H, F, fluorinated C₁-C₄ alkyl, C₄-C₂₀ aryl or fluorinated C₄-C₂₀ aryl. More preferably each of R₂, R₃ and R₄ is independently H, F, trifluoromethyl, phenyl, 4-methylphenyl, methyl, *n*-butyl, 4-*tert*-butylphenyl, 3,5,-di(trifluoromethyl)phenyl, 3,5,-dimethylphenyl, 2,4,6-tri(trifluoromethyl)phenyl, 4-(triisopropylsilyl)-2,6-di(trifluoromethyl)phenyl, *tert*-butyl, cyclohexyl or pentafluorophenyl.

15

Preferably L is a halide or a moiety of the formula -Z₃-R₁₁, C₁-C₁₀ alkyl, fluorinated C₁-C₁₀ alkyl, C₄-C₂₀ aryl or fluorinated C₄-C₂₀ alkyl; more preferably L is F, pentafluorophenyl, or a moiety of the formula -Z₃-R₁₁.

20

Preferably d is an integer from 0 to 6, more preferably an integer from 0 to 4, and most preferably d is 0 or 2.

Preferably e is an integer from 1 to 4, more preferably an integer from 1 to 2 and most preferably e is 2.

25

Preferably, the sum of d and e is an integer from 1 to 6, more preferably 2 to 4.

Preferably R₁₁ is fluorinated C₁-C₁₀ alkyl.

30

Preferably R₉ is substituted or unsubstituted P₁,P₂-substituted arylene or fluorinated arylene, or substituted or unsubstituted P₁,P₂-substituted cycloalkylene or fluorinated cycloalkylene, such as cyclopentylene, and preferably cyclohexylene. As used in this invention,

P₁,P₂-substituted arylene/cycloalkylene refers to an arylene/cycloalkylene moiety in which -Z₁-R₈- and -Z₂-R₁₀- groups are in P₁- and P₂-positions of the arylene/cycloalkylene moiety, respectively. Thus, for example, 1,2-substituted phenylene refers to a phenylene group having -Z₁-R₈- in the 1-position of the phenyl ring and -Z₂-R₁₀- group in the 2-position of the phenyl ring. "Substituted or unsubstituted" refers to the presence or absence of one or more substituents on the phenyl (or other appropriate) ring moiety, respectively. Such substituents can be F, Cl; Br; I; an alkyl group including cyclic alkyl and alkyl groups containing F, Cl, Br and/or I; and an aryl group including aryl groups containing F, Cl, Br and/or I and heteroaryl groups. For an electrolyte, R₉ can also be C₁-C₄ alkylene or fluorinated C₁-C₄ alkylene, in particular -C(CF₃)₂- moiety.

Preferably x is a bond or 1.

Preferably each of R₁₂ and R₁₃ are independently fluorinated C₁-C₄ alkyl. More preferably R₁₂ and R₁₃ are independently trifluoromethyl or perfluoroethyl, most preferably R₁₂ and R₁₃ are trifluoromethyl.

Alkyl groups according to the present invention are aliphatic hydrocarbons which can be straight or branched chain groups. Alkyl groups optionally can be substituted with one or more substituents, such as Cl, Br, I, alkenyl, alkynyl, aryl, hydroxy, alkoxy, carboxy, oxo or cycloalkyl. There may be optionally inserted along the alkyl group one or more oxygen, sulfur or substituted or unsubstituted nitrogen atoms. Exemplary alkyl groups include methyl, ethyl, *i*-propyl, *n*-butyl, *t*-butyl, chloromethyl, trichloromethyl, and pentafluoroethyl. Alkyl groups containing at least one fluorine is specifically referred herein as fluorinated alkyl groups.

Aryl groups are carbocyclic or heterocyclic aromatic ring moieties. Aryl groups can be substituted with one or more substituents, such as a Cl, Br, I, alkenyl, alkyl, alkynyl, hydroxy, alkoxy or cycloalkyl. Exemplary aryl groups include, phenyl, *p*-methylphenyl, *p*-*tert*-butylphenyl, thienyl, furanyl, pyrimidinyl, pyridyl, oxazolyl, isoxazolyl, and thiophenyl. Aryl groups containing at least one fluorine is specifically referred herein as fluorinated aryl groups.

M₁ of the polyfluorinated anion of the present invention may contain a mixture of polyfluorinated alkoxide and non-fluorinated alkoxide ligands.

Specific polyfluoroalkoxide ligands for anion of formula I (i.e., compound of formula III), include, but are not limited to, the following ligands:

5 a polyfluoroalkoxide ligand where Z is O, R₁ is methylene, b and c are 0, a is 4, and R₂, R₃ and R₄ are F; and

polyfluoroalkoxides where Z is O and R₁ is a bond, and

R₂ is trifluoromethyl, and each of R₃ and R₄ is independently phenyl or methyl;


10 R₂, R₃ and R₄ are trifluoromethyl;


R₂ is trifluoromethyl, R₃ is phenyl, and R₄ is phenyl or pentafluorophenyl; and

R₂ and R₃ are phenyl, and R₄ is pentafluorophenyl.

15 Specific polyfluoroalkoxide ligands for anion of formula II (i.e., compound of formula IV), include, but are not limited to, the following ligands:

n is 1 and the -Z₁-R₈-R₉-R₁₀-Z₂- moiety comprises:





where each of R_{14} , R_{15} , R_{16} , and R_{17} is independently H, C_1 - C_{10} alkyl, fluorinated C_1 - C_{10} alkyl, C_4 - C_{20} aryl, or fluorinated C_4 - C_{20} aryl. Preferably, R_{14} and R_{17} are trifluoromethyl, R_{15} is H, and R_{16} is phenyl.

Unlike other anions containing chelating dialkoxide groups, compounds II and IV of the present invention have improved stability (thermal, hydrolytic and electrochemical) lower toxicity, and/or higher synthetic yields. Moreover, compounds of the present invention, in particular lithium salts, have high conductivity making them particularly useful as electrolytes in electrochemical devices.

A variety of counter-cation species, including metal cations such as Li, K, Na, Mg, Ca, and Cs; trityl cation; pyridinium cations such as 2,6-pyridinium cation; and 2,6-lutidinium cation, can be prepared from the anions of the present invention. For example, by cation-exchange reaction, the trityl (CPh_3^+) salt can be prepared by metathesis of Li salt of the anions with CPh_3Cl in 1,2-dichloroethane.

Without being bound by any theory, it is believed that the high conductivity of lithium salts of the compounds of the present invention is due to Li^+ ion being weakly bonded to several alkoxide oxygen atoms and possibly being bonded to several CF_3 -group fluorine atoms, similar to Tl^+ ions in $Tl_2Zr(HFIP)_6$. In contrast, the Li^+ ion in the unfluorinated salt $LiNb(OEt)_6$ is believed to be strongly bonded to only four ethoxide oxygen atoms from two adjacent $Nb(OEt)_6^-$ anions forming a pseudo-tetrahedral LiO_4 core.

Compounds containing the polyfluorinated anion of the present invention have high electrical conductivity making them particularly useful as electrolytes for electrochemical devices. Exemplary electrochemical devices include batteries, such as lithium batteries or lithium ion batteries for a variety of applications; other type of batteries; fuel cells; electrical double layer capacitors; sensors; and electrochromic displays. Such electrochemical devices can be used in a variety of applications including electrochemical devices for electric vehicles, lap top computers, and other applications

requiring an energy source. As table 1 shows, lithium salts of the polyfluorinated anions of the present invention have high electrical conductivities in organic solvents. Specifically, the compounds of the present invention have high electrical conductivity in DME compared to other fluorine-containing lithium salts such as LiOTf.

5 Table 1. Electrical Conductivity¹

Compound	Conc. (M)	Solvent	Conductivity (mS cm ⁻¹)	Eq. Conductivity (S cm ² mol ⁻¹)
Li(HFIP)	0.0100	DME	~0	
LiOTf	0.0100	DME	0.00390	0.390
LiOTf/1.36 eq. crown	0.0100	DME	0.00700	0.700
LiOTf/>50 eq. crown	0.0100	DME	0.0310	3.10
LiOTf	0.0100	PC	0.195	19.5
LiB(C ₆ F ₅) ₃ (HFIP)	0.0100	DME	0.176	17.6
LiB(C ₆ F ₅) ₃ (DPTE)	0.0100	DME	0.129	12.9
LiB(C ₆ F ₅) ₃ (PFTB)	0.0100	DME	0.137	13.7
LiB(HFPOP) ₂	0.0100	DME	0.137	13.7
LiB(HFPOP) ₂	0.100	DME	1.58	15.8
LiB(HFPOP) ₂	0.200	DME	3.05	15.2
LiB(HFPOP) ₂	0.300	DME	4.49	15.0
LiB(HFPOP) ₂	0.400	DME	5.30	13.2
LiB(HFPOP) ₂	0.500	DME	5.88	11.8
LiB(HFPOP) ₂	0.600	DME	5.83	9.7
LiB(HFPOP) ₂	0.0100	PC	0.133	13.3
LiB(HFAPOP) ₂	0.0100	DME	0.160	16.0
LiB(HFAPOP) ₂	0.100	DME	1.77	17.7
LiB(HFAPOP) ₂	0.300	DME	4.22	14.1
LiB(HFAPOP) ₂	0.500	DME	4.35	8.69
LiB(HFTPOP) ₂	0.0100	DME	0.218	21.8
LiB(HFTPOP) ₂	0.500	DME	8.23	16.5
LiAl(HFIP) ₄	0.0100	DME	0.183	18.3
LiAl(TFTB) ₄	0.0100	DME	0.0693	6.93
LiAl(DPTE) ₄	0.0100	DME	0.205	20.5

¹ HFIP⁻ = OCH(CF₃)₂⁻; DPTE⁻ = OC(CF₃)(C₆H₅)₂⁻; TFTB⁻ = OC(CF₃)(CH₃)₂⁻; PFTB⁻ = OC(CF₃)₃⁻; HFPOP⁻² = OC(CF₃)₂(C₆H₄O)⁻²; HFAPOP⁻² = OC(CF₃)₂[C₆H₂(CH₃)(C₄H₉O)]⁻²; HFTPOP⁻² = OC(CF₃)₂(C₆HF₃O)⁻²; OTf = CF₃SO₃⁻; crown = 12-crown-4; PC = propylene carbonate; DME = 1,2-dimethoxyethane.

Particularly useful lithium salts of the compounds of the present invention in batteries include LiB(HFPOP)₂, LiB(HFAPOP)₂, and LiB(HFTPOP)₂.

Again referring to Table 1, the lithium salts of the polyfluorinated anions of the present invention are at least about two orders of magnitude higher in electrical conductivity than lithium triflate. Thus, the amount of a compound of the present invention required in an electrochemical device to achieve a similar electrical conductivity in an organic solvent such DME is about 1% of the amount of other fluorine-containing electrolytes such as LiCF_3SO_3 .

A lithium salt of the polyfluorinated anion of the present invention has an electrical conductivity of at least about $4 \text{ } \square \text{Scm}^{-1}$ in DME at about 0.01 M concentration at about $25 \text{ } \square \text{C}$, preferably at least about $60 \text{ } \square \text{Scm}^{-1}$, more preferably at least about $150 \text{ } \square \text{Scm}^{-1}$, and most preferably at least about $180 \text{ } \square \text{Scm}^{-1}$.

Without being bound by any theory, it is believed that the weak bonds between the Li^+ cation and the CF_3 groups are responsible for the high electrical conductivity in low dielectric solvents. Indeed, it is believed that the high degree of fluorination and the weak coordination between the Li^+ cations in the C-F bonds differentiate the lithium salts of the present invention from other fluorine-containing lithium salts.

The electrochemical stability of a representative compound is shown in Table 2 below. Specifically, Table 2 lists anodic stability of a compound containing a chelating group HFTPOP, *e.g.*, a bidentate group. The anodic stability shows the relative stability of the compound and the potential for oxidation of an anode containing the compound relative to lithium.


Table 2. Anodic Stability

Compound	Solvent	Conc. (M)	Potential vs. Li/Li^+ (V)
LiB(HFTPOP)_2	DME	0.1	4.7
LiAl(HFPP)_4	DME	0.07	>5.2

Conditions: Sweep rate: 5 mV/s; $T=25 \text{ } \square \text{C}$; Reference electrode: Li wire; Working electrode Pt; Counter electrode: Pt mesh.

The polyfluorinated anions of the present invention can also be used in a variety of organic reaction catalysts where a weakly coordinating anion improves the yield, selectivity and/or the rate of catalytic reaction by the corresponding cation including in catalysts for conjugate additions and Diels-Alder reactions. The compounds of the present invention comprise a weakly coordinating anion, *i.e.*, polyfluorinated anion, which

enhances the catalytic activity of the associated metal cation. Exemplary catalytic reactions that have recently received a considerable attention are lithium-catalyzed Diels-Alder reactions and lithium-catalyzed 1,4-conjugate addition reactions. As shown below, using $\text{LiNb}(\text{HFIP})_6$, **1**, as a catalyst in 1,4-conjugate addition reaction of silyl ketene acetal **2** to the sterically encumbered α,β -unsaturated carbonyl compound **3** gave the 1,4-addition product **4** in 93% yield.



Reaction conditions: 1,2-dichloroethane (DCE) solvent, 0.1 M of **3**, 0.2 M of **2**, 0.01 M of $\text{LiNb}(\text{HFIP})_6$ and 0.01 M of hexamethylphosphoramide (HMPA) at 24 °C for 30 hours.

Formation of only the 1,4-addition product **4** was observed under these conditions. Interestingly, when HMPA was left out of the reaction mixture, a mixture of **4** and the 1,2-addition product **5** was observed after only 10 minutes (95% isolated yield, 4:5 mole ratio = 1:5). Without being bound by any theory, it is believed that Li^+ ion coordinates with HMPA to produce a sterically more hindered enone-lithium ion complex, thus favoring addition of the ketene at a site more distant from the carbonyl carbon, *i.e.*, 1,4-addition, over addition of the ketene to the carbonyl carbon, *i.e.*, 1,2-addition reaction. Because lithium compounds of the present invention are similar to lithium compounds disclosed in PCT Patent Application No. PCT/US98/19268 and U.S. Patent Application No. 09/151,852, lithium compounds of the present invention are expected to provide a similar reaction selectivity.

A comparison of the ability of $\text{LiNb}(\text{HFIP})_6$ and two other lithium catalysts to increase the formation of 1,4-conjugate addition product is shown in Table 3. The weaker Lewis acidity of the $\text{Li}(\text{HMPA})^+$ complex results in a decreased reaction rate, which is evidenced by the longer reaction time required when HMPA is added to the reaction mixture. The results obtained with $\text{LiNb}(\text{HFIP})_6$ are comparable to the results obtained with the very active catalyst $\text{LiCo}(\text{C}_2\text{B}_9\text{H}_{11})_2$. Product yields were substantially lower

when LiClO_4 was the catalyst. Furthermore, when LiClO_4 was employed in the presence of co-catalyst HMPA, the ratio of 4:5 improved only to 1.3:1. Without being bound by any theory, it is believed that the larger size and/or more weakly coordinating ability of $\text{Nb}(\text{HFIP})_6^-$ to Li^+ compared with ClO_4^- is responsible for the difference in catalytic activity between LiClO_4 and $\text{LiNb}(\text{HFIP})_6$.

Table 3. Yields of 1,4- and 1,2-addition products 4 and 5, respectively, from lithium-catalyzed reactions between 2 and 3^a

catalyst	co-catalyst ^b	time	4:5 ratio	% yield
$\text{LiNb}(\text{HFIP})_6$	none	10 min	1:5	95%
$\text{LiNb}(\text{HFIP})_6$	0.1 M HMPA	30 h	100:0	93%
$\text{LiCo}(\text{C}_2\text{B}_9\text{H}_{11})_2^c$	none	20 min	1:6	95%
$\text{LiCo}(\text{C}_2\text{B}_9\text{H}_{11})_2^c$	0.1 M HMPA	32 h	100:0	96%
LiClO_4	none	10 min	1:4.5	62%
LiClO_4	0.1 M HMPA	48 h	1.3:1	69%

a Reaction conditions: 1,2-dichloroethane, 0.1 M of 3, 0.2 M of 2, 0.1 M of catalyst and 0.1 M of co-catalyst, when appropriate, at 25 °C).

b HMPA = hexamethylphosphoramide.

c These results are from DuBay *et al.*, *J. Org. Chem.*, **1994**, *59*, 6898.

The polyfluorinated anions of the present invention that are sterically bulkier, *i.e.*, larger, than $\text{Nb}(\text{HFIP})_6^-$ afford lithium-ion catalysts that are more regioselective and/or more active in the absence of HMPA. Moreover, enantiomerically enriched polyfluorinated anions of the present invention containing a polyfluorinated alkoxide having a chiral center afford lithium-ion catalysts that are enantioselective, *i.e.*, produce an enantiomerically enriched product. A chiral center of a carbon atom, of course, is a carbon atom to which four different groups are attached; however, the ultimate criterion of chirality of a compound is nonsuperimposability on the mirror image. Facially selective, enantioselective or stereoselective synthetic reactions are those in which one of a set of stereoisomers is formed predominantly or exclusively. Preferably, one isomer is produced in at least about 50 percent enantiomeric excess. Enantiomeric excess is the amount of difference between one enantiomer and the other enantiomer in the product composition. Enantiomeric excess can be expressed by the following formula: $\%ee = (R-S)/(R+S)$, where R is amount of one enantiomer and S is the amount of the other enantiomer, for

example, %ee of a product composition containing 98% of one enantiomer and 2% of the other enantiomer is 96%. More preferably, one isomer is produced in at least about 80 percent enantiomeric excess, still more preferably at least about 90 percent enantiomeric excess, even more preferably at least about 95 percent enantiomeric excess, and most
5 preferably at least about 98 percent excess over the other enantiomer.

Lithium salts of the polyfluorinated anions of the present invention can be combined or mixed with a polymer to prepare polymeric materials that exhibit lithium ion conductivity. Such materials, referred to as salt-in-polymer solid electrolytes or solid
10 polymer electrolytes, can be used as electrolytes for solvent-free high-energy-density lithium-based batteries. A polymer can also include a linker which allows a direct linkage of the compound of the present invention to the polymeric structure by a chemical bond formation between the polymer and the compound of the present invention. The polymers useful for the present invention have a rubbery physical characteristic. Generally, suitable polymers have one or more of the following identifying characteristics: 1) ability to
15 dissolve lithium salts of weakly coordinating anions and/or to coordinate, albeit weakly, to the lithium cations of lithium salts of weakly coordinating anions; 2) ability to maintain low glass-transition temperatures with varying amounts of lithium salts dissolved therein; and 3) the ability to possess high electrical conductivities, especially high lithium-ion conductivities, *i.e.*, higher than lithium triflate/polymer mixture at a given temperature).
20 Exemplary polymers useful for the present invention include polyethylene glycol; polyethylene; polypropylene; polystyrene; polybutadiene; poly(vinyl fluoride); polychloroprene; poly(alkyl siloxane) such as poly(dimethylsiloxane); poly(vinyl chloride); poly(ethylene imine); and poly(alkylene oxide) such as poly(propylene oxide), amorphous poly(ethylene oxide) and poly(ethylene oxide). Preferably the polymer is selected from
25 the group consisting of amorphous polyethylene oxide (aPEO), poly(alkylene oxide), poly(alkyl siloxane), poly(vinyl fluoride), poly(vinyl chloride), polychloroprene, polybutadiene, polyethylene and poly propylene; more preferably from the group consisting of aPEO, poly(vinyl fluoride), poly(vinyl chloride), polychloroprene, polybutadiene, polyethylene and polypropylene; and most preferably from the group
30 consisting of aPEO, polybutadiene, polyethylene and polypropylene.

The present invention also includes salt-in-polymer electrolytes having alkali metal salts containing the polyfluorinated anions of the present invention. Compounds containing these polyfluorinated anions have superior glass transition temperatures, impedance measurements and cation transference numbers than compounds containing
5 other anions.

The polyfluorinated anions of the present invention can also be used as co-catalysts for activating transition-metal-catalyzed olefin polymerization and as counterions for polymerization photoinitiators.

Additional objects, advantages, and novel features of this invention will become
10 apparent to those skilled in the art upon examination of the following examples thereof, which are not intended to be limiting.

EXAMPLES

Example 1

15 Synthesis of $\text{LiB}(\text{C}_6\text{F}_5)_3(\text{HFIP})$.

$\text{B}(\text{C}_6\text{F}_5)_3$ (0.0256 g, 0.05 mmol) and LiHFIP (0.0087 g, 0.05 mmol) were dissolved in 5 mL of DME to make a clear, colorless solution.

Example 2

Synthesis of $\text{LiB}(\text{C}_6\text{F}_5)_3(\text{DPTE})$.

20 $\text{B}(\text{C}_6\text{F}_5)_3$ (0.0256 g, 0.05 mmol) and LiDPTE (0.0129 g, 0.05 mmol) were dissolved in 5 mL of DME to make a clear, colorless solution.

Example 3

Synthesis of $\text{LiB}(\text{C}_6\text{F}_5)_3(\text{PFTB})$.

25 $\text{B}(\text{C}_6\text{F}_5)_3$ (0.0256 g, 0.05 mmol) and LiPFTB (0.0121 g, 0.05 mmol) were dissolved in 5 mL of DME to make a clear, colorless solution.

Example 4

Synthesis of $\text{LiAl}(\text{DPTE})_4$.

30 Hexane (40 mL) was added to LiAlH_4 (0.0188 g, 0.4955 mmol) to make a suspension. To this was added $\text{H}(\text{DPTE})$ (0.500 g, 1.982 mmol) as a hexane solution (10 mL). The reaction mixture was stirred for 4 day at room temperature under an argon atmosphere, after which time a considerable amount of a white solid material was present

in a clear and colorless solution. The mixture was filtered through a medium frit. The white solid was washed with hexane, then dissolved in toluene. Toluene was removed under vacuum to leave a white solid that was heated at 105 °C for 18 h. A ^1H NMR spectrum of this white solid revealed that approximately 3 mol-% of the alcohol H(DPTE) still remained, but the compound $\text{LiAl}(\text{DPTE})_4$ was otherwise pure.

^1H NMR ($\text{C}_6\text{D}_6/\text{C}_6\text{F}_6$) δ 7.26 (d, 16 H), 7.00 (m, 24 H). ^{19}F NMR($\text{C}_6\text{D}_6/\text{C}_6\text{F}_6$) δ -72.40 (s). Low Resolution mass spectrum (negative ion electrospray, CH_3CN solution): m/z 1031 (M-Li^-); calc'd for $\text{C}_{56}\text{H}_{40}\text{AlF}_{12}\text{O}_4$ 1031.6.

Example 5

10 Synthesis of $\text{Li}(\text{DME})_2\text{Al}(\text{TFTB})_4$.

Hexane (30 mL) was added to LiAlH_4 (0.0976 g, 2.57 mmol) to make a suspension. To this was added H(TFTB) (1.3155 g, 10.28 mmol) as a hexane solution (20 mL). The reaction mixture was stirred for 3 day at room temperature then at reflux for 3 days under an argon atmosphere. After this time almost no solid was present in solution. The mixture was filtered through a medium frit, to leave an off-white solid and a slightly tan, clear solution. Hexane was removed from the latter under vacuum to leave a white solid. This was sublimed at 90 °C under vacuum to yield a white powder. The solid was dissolved in DME and stirred for 2 h, after which time solvent was removed to yield a white powder.

20 ^1H NMR ($\text{C}_6\text{D}_6/\text{C}_6\text{F}_6$) δ 2.89 (DME, s, 6 H), 2.68 (DME, s, 4 H), 1.53 (s, 12 H). ^{19}F NMR($\text{C}_6\text{D}_6/\text{C}_6\text{F}_6$) δ -84.62 (s).

Example 6

Synthesis of $\text{LiAl}(\text{HFIP})_4$.

Freon-113 (40 mL) was added to LiAlH_4 (0.1630 g, 4.29 mmol) to make a suspension. This was cooled to 0 °C in an ice bath, and H(HFIP) (2.8826 g, 17.16 mmol) was added dropwise as a solution in 10 mL Freon-113. This mixture was stirred at 0 °C for 24 h, then at room temperature for 4 days. After this time, the solution was white and cloudy. Freon-113 was removed under vacuum to leave a white solid, which was found to be 97.4% pure by ^{19}F NMR.

30 ^1H NMR ($\text{CD}_3\text{CN}/\text{C}_6\text{F}_6$) δ 4.6 (m, 4 H). ^{19}F NMR($\text{CD}_3\text{CN}/\text{C}_6\text{F}_6$) δ -76.15 (d). Low Resolution mass spectrum (negative ion electrospray, CH_3CN solution): m/z 694.9 (M-Li^-).

Li)⁺; calc'd for C₁₂H₄AlF₂₄O₄ 695.1.

Example 7

Synthesis of LiB(HFPOP)₂.

H₂(HFPOP) (2.0029 g, 7.7 mmol), LiOH•H₂O (0.1541 g, 3.67 mmol), and
5 B(OH)₃ (0.2267, 3.67 mmol) were dissolved in 115 mL distilled water. Under an argon atmosphere, the mixture was stirred at 105 °C for 18 h. After this time, the solution was clear and colorless. It was opened to air, and water was removed using a rotary evaporator to leave a clear, colorless oil. This was first dried by azeotropic distillation with toluene to leave a white powder, followed by heating at 197 °C under vacuum (10⁻³
10 torr) for a period of 18 h. Yield: 1.7856 g (91%) isolated as a white solid.

¹H NMR (CD₃CN/C₆F₆) δ 7.37 (d, 2 H), 7.24 (t, 2 H), 6.79 (t, 2H), 6.7 (d, 2 H). ¹⁹F NMR(CD₃CN/C₆F₆) δ -75.00 (s). Low Resolution mass spectrum (negative ion electrospray, CH₃CN solution): m/z 527.1 (M-Li)⁻; calc'd for C₁₈H₈BF₁₂O₄ 527.0.

Example 8

15 Synthesis of LiB(HFAPOP)₂.

LiOH•H₂O (0.1522 g, 3.62 mmol) and B(OH)₃ (0.2241 g, 3.62 mmol) were dissolved in 115 mL distilled water and heated at reflux for 18 h. H₂(HFAPOP) (2.5120 g, 7.61 mmol) was then added as a solid along with diethyl ether (15 mL). This mixture was heated to 100 °C and stirred for 18 h. After this time, the reaction mixture was a
20 clear and colorless solution. Diethyl ether and water were removed using a rotary evaporator to leave a clear, colorless oil. This was first dried by azeotropic distillation with toluene to leave an off-white powder, followed by heating at 104 °C under high-vacuum conditions (10⁻⁵ torr) for 7 days. Yield: 1.9749 g (82 %) isolated as an off-white solid.

25 ¹H NMR (C₆D₆/C₆F₆) δ 7.37 (m, 2 H), 7.133 (s, 1 H), 7.127 (s, 1 H), 2.07 (s, 6 H), 1.27 (s, 18 H). ¹⁹F NMR(C₆D₆/C₆F₆) δ -72.81 (m), -76.44 (m). Low Resolution mass spectrum (negative ion electrospray, CH₃CN solution): m/z 667.3 (M-Li)⁻; calc'd for C₂₈H₂₈BF₁₂O₄ 667.1.

Example 9

30 Synthesis of LiB(HFTPOP)₂.

LiOH•H₂O (0.156 g, 3.72 mmol) and B(OH)₃ (0.230 g, 3.72 mmol) were

dissolved in 50 mL distilled water and heated at reflux for 1 h. The compound $\text{H}_2(\text{HFTPOP})$ (2.45 g, 7.44 mmol) was then added as a solid along with diethyl ether (10 mL). This mixture was heated to 100 °C and stirred for 18 h. After this time, the reaction mixture was a clear and colorless solution. Diethyl ether and water were removed using a rotary evaporator to leave a clear, colorless oil. This was first dried by azeotropic distillation with toluene, followed by heating at 190 °C under high-vacuum conditions (10^{-3} torr) for 18 h. Yield: 2.08 g (87%).

^1H NMR ($\text{CD}_3\text{CN}/\text{C}_6\text{F}_6$) δ 7.12 (m, 2 H). ^{19}F NMR($\text{CD}_3\text{CN}/\text{C}_6\text{F}_6$) δ -75.42 (s), -148.75 (m), -157.38 (m). Low Resolution mass spectrum (negative ion electrospray, CH_3CN solution): m/z 634.8 (M-Li^-); calc'd for $\text{C}_{18}\text{H}_2\text{BF}_{18}\text{O}_4$ 635.0.

Example 10

This example illustrates a method for preparing salt-in-polymer electrolytes containing the polyfluorinated anion of the present invention.

Samples of aPEO containing different stoichiometric amounts of $\text{LiNb}(\text{HFIP})_6$ were prepared as follows. A sample of the polymer (typically 0.13 g, 3.0 mmol ether-oxygen atoms) was mixed with tetrahydrofuran (7 mL). The resulting mixture was mixed with a tetrahydrofuran solution containing varying amounts of $\text{LiNb}(\text{HFIP})_6$ so that the ether-oxygen/lithium molar ratio was 12, 24, or 30. The reaction mixture was stirred for 15 hours, after which time a colorless homogeneous solution was observed. Volatiles were removed from the reaction mixture by vacuum evaporation, resulting in a clear, colorless, rubbery solid on the walls of the flask. The rubbery solid was heated under vacuum at 60 °C for 12 hours to ensure complete removal of tetrahydrofuran. The three clear, colorless, rubbery, salt-in-polymer electrolytes prepared in this way were $\text{aPEO}_{12}\text{LiNb}(\text{HFIP})_6$, $\text{aPEO}_{24}\text{LiNb}(\text{HFIP})_6$, and $\text{aPEO}_{30}\text{LiNb}(\text{HFIP})_6$.

Example 11

Synthesis of $\text{LiAl}[\text{O}(\text{C}_6\text{H}_4)\text{C}(\text{CF}_3)_2\text{O}]_2$

About 0.515 g of $\text{HO}(\text{C}_6\text{H}_4)\text{C}(\text{CF}_3)_2\text{OH}$ (1.98 mmol) and 0.155 g of LiAlH_4 (4.09 mmol) were mixed in toluene and stirred for 140 h. The reaction mixture was filtered through a Schlenk filter with Celite. The filtrate was concentrated under vacuum to leave a brown solid.


^1H NMR (C_6D_6) δ 7.76 (doublet, 1 H), 7.37 (doublet, 1 H), 6.93 (triplet, 1 H), 6.73

(triplet, 1 H), 6.65 (triplet, 1 H), 6.56 (triplet, 1 H), 6.45 (doublet, 1 H), 6.03 (doublet, 1 H). ^{19}F NMR (C_6D_6) \square -72.47 (multiplet), -74.06 (multiplet), -78.15 (multiplet), -78.75 (multiplet).

5 The foregoing discussion of the invention has been presented for purposes of illustration and description. The foregoing is not intended to limit the invention to the form or forms disclosed herein. Although the description of the invention has included description of one or more embodiments and certain variations and modifications, other variations and modifications are within the scope of the invention, *e.g.*, as may be within the skill and knowledge of those in the art, after understanding the present disclosure. It
10 is intended to obtain rights which include alternative embodiments to the extent permitted, including alternate, interchangeable and/or equivalent structures, functions, ranges or steps to those claimed, whether or not such alternate, interchangeable and/or equivalent structures, functions, ranges or steps are disclosed herein, and without intending to publicly dedicate any patentable subject matter.

WHAT IS CLAIMED IS:

1. A compound comprising a monoanion of the formula:




wherein

- 5 M_1 is a transition metal, or a Group III, IV or V element provided M_1 is not Cu;
- each Z is independently O, S, or NR_6R_7 ;
- each X is independently a halide;
- each R_1 is independently a bond or C_1 - C_4 alkylene;
- 10 each of R_2 , R_3 and R_4 is independently H, F, fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl, C_3 - C_{10} cycloalkyl, fluorinated C_3 - C_{10} cycloalkyl, C_1 - C_{10} alkyl or C_4 - C_{20} aryl, provided at least one of R_2 , R_3 and R_4 is F, fluorinated C_1 - C_{10} alkyl, fluorinated C_3 - C_{10} cycloalkyl, or fluorinated C_4 - C_{20} aryl;
- each R_5 is independently fluorinated C_1 - C_{10} alkyl, fluorinated C_4 - C_{20} aryl,
- 15 C_4 - C_{20} aryloxy, fluorinated C_4 - C_{20} aryloxy, C_1 - C_{10} alkoxide or fluorinated C_1 - C_{10} alkoxide;
- each of R_6 and R_7 is independently H or C_1 - C_{10} alkyl; and
- each of a, b and c is independently an integer from 0 to 4,
- provided the sum of a, b and c is an integer from 2 to 8; and
- 20 provided that when R_2 is a fluorinated C_1 - C_4 alkyl, R_1 is a bond, b, and c are 0, and R_3 is C_1 - C_{10} alkyl or fluorinated C_1 - C_{10} alkyl then R_4 is F, fluorinated C_1 - C_{10} alkyl or fluorinated C_4 - C_{20} aryl.
2. The compound of Claim 1, wherein M_1 is selected from the group consisting of Al, B, V, Ti, Si, Zr, Cu, Ge, Sn, Y, Zn, Ga, Nb, Ta, Bi, P, As, Sc, Hf and
- 25 Sb.
3. The compound of Claim 2, wherein M_1 is selected from the group consisting of Al, B, Nb and Ta.

4. The compound of Claim 3, wherein M_1 is selected from the group consisting of Al and B.
5. The compound of Claim 1, wherein X is F.
6. The compound of Claim 1, wherein R_5 is pentafluorophenyl.
- 5 7. The compound of Claim 1, wherein Z is O and R_1 is a bond.
8. The compound of Claim 7, wherein
 R_2 is trifluoromethyl, and each of R_3 and R_4 is independently phenyl or methyl;
 R_2 , R_3 and R_4 are trifluoromethyl;
 R_2 is trifluoromethyl, R_3 is phenyl, and R_4 is phenyl or pentafluorophenyl; or
10 R_2 and R_3 are phenyl, and R_4 is pentafluorophenyl.
9. The compound of Claim 1, wherein R_5 is 2-trifluoromethyl-phenoxide, 3-trifluoromethylphenoxide, 4-trifluoromethylphenoxide, pentafluorophenoxide, or pentafluorophenyl.
10. The compound of Claim 1, wherein the sum of a, b and c is 4.
- 15 11. The compound of Claim 1, wherein Z is O and R_1 is methylene.
12. The compound of Claim 11, wherein b and c are 0, a is 4 and R_2 , R_3 and R_4 are F.
13. An electrolyte for an electrochemical device comprising the compound of Claim 1.
- 20 14. The electrolyte of Claim 13, wherein the counter cation of said monoanion is lithium.

15. A compound comprising an anion of the formula:



wherein

M_1 is a transition metal, or a Group III, IV or V element;

L is a halide, $\text{C}_1\text{-C}_{10}$ alkyl, fluorinated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_4\text{-C}_{20}$ aryl, fluorinated $\text{C}_4\text{-C}_{20}$ alkyl or a moiety of the formula $-\text{Z}_3\text{-R}_{11}$;

d is an integer from 0 to 4;

e is an integer from 1 to 3;

the sum of d and e is an integer from 1 to 6;

n is 1 or 2;

each of Z_1 , Z_2 and Z_3 is independently O, S, or NR_6R_7 ;

each of R_6 and R_7 is independently H or $\text{C}_1\text{-C}_{10}$ alkyl;

each R_9 is independently $\text{C}_1\text{-C}_{30}$ alkylene, fluorinated $\text{C}_1\text{-C}_{30}$ alkylene, substituted $\text{C}_1\text{-C}_{30}$ alkylene, $\text{C}_3\text{-C}_{10}$ cycloalkylene, fluorinated $\text{C}_3\text{-C}_{10}$ cycloalkylene, $\text{C}_4\text{-C}_{20}$ arylene or fluorinated $\text{C}_4\text{-C}_{20}$ arylene;

each of R_8 and R_{10} is a bond, or a moiety of the formula $-\text{C}(\text{R}_{12}\text{R}_{13})_x$;

each x is independently an integer from 1 to 4;

each of R_{12} and R_{13} is independently H, F, $\text{C}_1\text{-C}_4$ alkyl or fluorinated $\text{C}_1\text{-C}_4$ alkyl; and

each R_{11} is independently $\text{C}_1\text{-C}_{10}$ alkyl, fluorinated $\text{C}_1\text{-C}_{10}$ alkyl, $\text{C}_4\text{-C}_{20}$ aryl, or fluorinated $\text{C}_4\text{-C}_{20}$ aryl;

provided at least one of R_8 and R_{10} is a moiety of the formula $-\text{C}(\text{R}_{12}\text{R}_{13})-$ and at least one of R_{12} and R_{13} is F or fluorinated $\text{C}_1\text{-C}_4$ alkyl.

16. The compound of Claim 15, wherein M_1 is selected from the group consisting of Al, B, V, Ti, Si, Zr, Ge, Sn, Cu, Y, Zn, Ga, Nb, Ta, Bi, P, As, Sc, Hf and Sb.

17. The compound of Claim 16, wherein M_1 is selected from the group consisting of Al, B, Nb and Ta.

18. The compound of Claim 17, wherein M₁ is selected from the group consisting of Al and B.


19. The compound of Claim 15, wherein R₁₂ and R₁₃ are fluorinated C₁-C₄ alkyl.

- 5 20. The compound of Claim 19, wherein R₁₂ and R₁₃ are trifluoromethyl.

21. The compound of Claim 15, wherein the sum of d and e is 2 or 4.

22. The compound of Claim 15, wherein n is 1, Z₁ and Z₂ are O, R₈ is a moiety of the formula -C(R₁₂R₁₃)-, R₁₀ is a bond, and R₁₂ and R₁₃ are trifluoromethyl.

23. The compound of Claim 15, wherein n is 1 and the -Z₁-R₈-R₉-R₁₀-Z₂-
10 moiety comprises:



wherein each of R₁₄, R₁₅, R₁₆, and R₁₇ is independently H, C₁-C₁₀ alkyl, fluorinated C₁-C₁₀ alkyl, C₄-C₂₀ aryl, or fluorinated C₄-C₂₀ aryl.

24. The compound of Claim 23, wherein R_{14} and R_{17} are trifluoromethyl, R_{15} is H, and R_{16} is phenyl.
25. The compound of Claim 15, wherein d is 0 and e is 2.
26. The compound of Claim 15, wherein d is 2 and e is 2.
- 5 27. The compound of Claim 15, wherein L is F.
28. The compound of Claim 15, wherein R_9 is C_4 - C_{20} arylene or fluorinated C_4 - C_{20} arylene.
29. An electrolyte for an electrochemical device comprising a compound of Claim 15.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/06293

A. CLASSIFICATION OF SUBJECT MATTER IPC(7) :Please See Extra Sheet. US CL :Please See Extra Sheet. According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 534/15; 556/1, 42, 54, 56, 64, 76, 81, 110, 113, 116, 118, 130, 176, 182, 186, 400, 407, 408, 410, 426, 464; 568/6, 12, 14, 16 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) REGISTRY and CA Databases		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	MEHROTRA et al. Metal β -diketonates and allied derivatives. London: Academic Press, 1978, see pages 42-44.	1, 2, and 13
X	GLOCKLING, F. The Chemistry of germanium. London: Academic Press, 1969, see page 35.	1, 2, and 13
X	MAITLIS, P.M. The Organic Chemistry of Palladium. New York: Academic Press, 1971, Volume II, page 97.	1, 2, and 13
X	COTTON et al. Advanced Inorganic Chemistry: A Comprehensive Text. New York: Wiley-Interscience Publication, 1980, fourth Edition, see pages 328, 448 and 709.	1-4, 10 and 13
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family	
Date of the actual completion of the international search 21 JUNE 2000		Date of mailing of the international search report 04 AUG 2000
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer Porfirio Nazario-Gonzalez Telephone No. (703) 308-1235

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/06293

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/06293

A. CLASSIFICATION OF SUBJECT MATTER:

IPC (7):

C07F 3/00, 5/00, 5/02, 5/06, 7/02, 7/22, 7/28, 7/30, 9/02, 9/66, 9/94,

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

534/15; 556/1, 42, 54, 56, 64, 76, 81, 110, 113, 116, 118, 130, 176, 182, 186, 400, 407, 408, 410, 426, 464; 568/6, 12, 14, 16

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be searched, the appropriate additional search fees must be paid.

Group I, claim(s) 1-14, drawn to a compound and/or electrolyte.

Group II, claim(s) 15-29, drawn to a compound and/or electrolyte.

The inventions listed as Groups I and II do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: each compound is structurally different from one another. For example, compounds of Group II are metal chelates whereas compounds of Group I are not. Thus, since one Group is not obvious over the other Group, each Group is distinct from one another.